



## Coating over Rubio Monocoat

Occasionally customers ask if they can apply polyurethane over our finish. While this takes away many of the benefits of our product, it can be done. This document relays the procedure as it has been described to us by customers.

Application of Rubio Monocoat Oil Plus or Oil Plus 2C;

1. Spread our product on the surface to be treated
2. Allow the product to react for minimum 3 minutes
3. Remove ALL excess oil by wiping the surface dry

Allow this application to dry completely; normally 72 hours with good airflow.

Surface Preparation for coat of polyurethane;

1. Using a 3M Surface Preparation Pad (SPP), buff the surface of the finish to lightly abrade.
2. Vacuum or tack any dust off
3. Apply the polyurethane like you would on any other application following the manufacturer's specifications.
4. It is highly advised that you check the adhesion on your preparation prior to application.

Please keep in mind that we make no recommendations, warranty, implied warranty, inferred warranty or any claims as to the suitability or performance of this procedure. We are also not responsible for your decision to do this or your results in any way. **IN FACT WE RECOMMEND THAT YOU NOT COAT OVER OUR FINISH.**

The preceding instructions are those as they have been relayed by customers and are not the advice of Rubio Monocoat, Muylle-Facon, Rubio Monocoat USA, LLC or any of its representatives, distributors, dealers and/or manufacturers.